

## CLAIMS

1. A process for the treatment of waste gas wherein the waste gas is contacted with a zeolite Y which has a unit cell size of 24.17-24.45 Å and a water adsorption capacity ( $p/p_0 = 0.2$ ,  $T=25^{\circ}\text{C}$ ) of at most 5 wt.%, characterised in that the zeolite has a silica-alumina molar ratio of at least 40.  
5
2. The process of claim 1 wherein the waste gas is engine exhaust gas, in particular exhaust gas from a diesel or gasoline engine.  
10
3. The process of any of the preceding claims, wherein the zeolite functions as an adsorbent which adsorbs organic hydrocarbons at a low temperature and desorbs them at a higher temperature.  
15
4. The process of claim 1 or 2 wherein the zeolite is part of an oxidation catalyst, the zeolite optionally comprising a noble metal of Group VIII of the periodic table of elements.
- 20 5. The process of claim 1 or 2 wherein the zeolite is part of a  $\text{NO}_x$  reducing catalyst and/or of a  $\text{NO}_x$  trap catalyst, the zeolite optionally comprising noble metal of Group VIII of the periodic table of elements and/or a non-noble metal of Group VIII of the periodic table and optionally an alkaline earth metal component such as barium.
- 25 6. A process for the treatment of exhaust gas from a diesel engine, wherein the engine exhaust system is provided with a hydrocarbon adsorbent and/or an oxidation catalyst and/or a  $\text{NO}_x$  conversion catalyst and/or a  $\text{NO}_x$  trap catalyst, wherein the hydrocarbon adsorbent and/or  
30 and or the oxidation catalyst and/or the  $\text{NO}_x$  conversion catalyst and/or

the NO<sub>x</sub> trap catalyst comprise a zeolite Y which has a unit cell size of 24.17-24.45 Å, a water adsorption capacity ( $p/p_0 = 0.2$ ,  $T=25^{\circ}\text{C}$ ) of at most 5 wt.% and a silica-alumina molar ratio of at least 40.

- 5    7.    The process of any of the preceding claims wherein the zeolite is periodically subjected to a temperature above 350°C.
8.    A unit suitable for the treatment of exhaust gas according to any one of the preceding claims, which comprises a zeolite Y which has a unit cell  
10    size of 24.17-24.45 Å, a water adsorption capacity ( $p/p_0 = 0.2$ ,  $T=25^{\circ}\text{C}$ ) of at most 5 wt.%, and a silica-alumina molar ratio of at least 40
9.    The unit of claim 8 which comprises a monolith at least part of the surface of which is coated with the zeolite.
- 15    10.    The unit of claim 8 or 9 which additionally comprises a Group VIII non-noble metal and/or a Group VIII noble metal, and/or an alkaline earth metal, and/or a Group I metal.